

Torlon® 4630

polyamide-imide

Torlon 4630 is an injection-moldable, wear-resistant grade of polyamide-imide (PAI), that has been formulated to give outstanding wear resistance in non-lubricated applications. Torlon PAI has the highest strength and stiffness of any thermoplastic up to 275°C (525°F). It has outstanding resistance to wear, creep and chemicals.

Potential applications for Torlon 4630 polyamide-imide include thrust washers, seal rings, sliding vanes, bobbins, bushings, clutch rollers and pistons.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	• South America
Additive	• PTFE + Graphite Lubricant		
Features	• Flame Retardant • Good Chemical Resistance • Good Creep Resistance	• Good Wear Resistance • High Heat Resistance • High Stiffness	• High Temperature Strength • Low Friction
Uses	• Automotive Applications	• Bearings	• Bushings
RoHS Compliance	• Contact Manufacturer		
Forms	• Pellets		
Processing Method	• Injection Molding	• Machining	• Profile Extrusion

Physical

	Typical Value	Unit	Test Method
Specific Gravity	1.56	g/cm ³	ASTM D792
Water Absorption (24 hr)	0.18	%	ASTM D570

Mechanical

	Typical Value	Unit	Test Method
Tensile Modulus	7450	MPa	ASTM D638
Tensile Strength	81.4	MPa	ASTM D638
Tensile Elongation (Break)	1.9	%	ASTM D638
Flexural Modulus	6830	MPa	ASTM D790
Flexural Strength	131	MPa	ASTM D790
Compressive Strength	99.3	MPa	ASTM D695
Coefficient of Friction			
-- 1	0.15		ASTM D1894
-- 2	0.030		ASTM D1894
-- 3	0.32		ASTM D3702
-- 4	0.32		ASTM D3702
Wear Factor			ASTM D3702

Dry: 0.25 m/s, 3.4 MPa (50 fpm, 500 psi)	6.00	in ³ ·min ⁻¹⁰ /ft·lb·hr
Dry: 4 m/s, 0.2 MPa (800 fpm, 31.25 psi)	13.5	in ³ ·min ⁻¹⁰ /ft·lb·hr
Lubricated: 0.375 m/s, 6.9 MPa (75 fpm, 1000 psi)	11.0	in ³ ·min ⁻¹⁰ /ft·lb·hr
Lubricated: 4 m/s, 5.2 MPa (800 fpm, 750 psi)	1.00	in ³ ·min ⁻¹⁰ /ft·lb·hr

Impact

	Typical Value	Unit	Test Method
Notched Izod Impact	48	J/m	ASTM D256

Impact	Typical Value	Unit	Test Method
Unnotched Izod Impact	160	J/m	ASTM D256
Thermal	Typical Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	279	°C	ASTM D648
Coefficient of Linear Thermal Expansion	3.6E-6	cm/cm/°C	ASTM D696
Injection	Typical Value	Unit	
Drying Temperature	177	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	304	°C	
Nozzle Temperature	371	°C	
Mold Temperature	199 to 216	°C	
Back Pressure	6.89	MPa	
Screw Speed	50 to 100	rpm	
Screw L/D Ratio	18.0:1.0 to 24.0:1.0		

Injection Notes

Minimum drying times are: 3 hours at 350°F (177°C), 4 hours at 300°F (149°C), or 16 hours at 250°F (121°C).

Compression Ratio between 1:1 and 1.5:1

Begin hold pressure at a high setting 6,000-8,000 psi (41.37-55.16 MPa), for several seconds, then drop off to 3,000-5,000 psi (20.69-34.48 MPa), for the duration of the hold pressure sequence.

Molded parts must be post cured.

Notes

Typical properties: these are not to be construed as specifications.

¹ Lubricated: 0.25 m/s, 6.9 MPa (75 fpm, 1000 psi)

² Lubricated: 4 m/s, 5.2 MPa (800 fpm, 750 psi)

³ Dry: 0.25 m/s, 3.4 MPa (50 fpm, 500 psi)

⁴ Dry: 4 m/s, 0.2 MPa (800 fpm, 31.25 psi)

www.SolvaySpecialtyPolymers.com

Contact Solvay Specialty Polymers

Europe, Middle East and Africa SpecialtyPolymers.EMEA@solvay.com
Americas SpecialtyPolymers.Americas@solvay.com
Asia and Australia SpecialtyPolymers.Asia@solvay.com

For assistance with an emergency involving this product, such as spill, leak, fire or explosion, call day or night:

Emergency Health Information

USA +1.800.621.4590
International +1.770.772.8577

Emergency Spill Information

USA +1.800.424.9300
+1.703.527.3887 (CHEMTREC)
Europe +44.208.762.8322 (CARECHEM)
China +86.10.5100.3039
All other Asian countries +65.633.44.177

For additional product information, technical assistance and Material Safety Data Sheets (MSDS), call:

USA + 1.800.621.4557 / +1.770.772.8760
Europe +49.211.5135.9000
Japan +81.3.5425.4300
China & Southeast Asia +86.21.5080.5080

Material Safety Data Sheets (MSDS) for products of Solvay Specialty Polymers are available upon request from your sales representative or by emailing us at specialtypolymers@solvay.com. Always consult the appropriate MSDS before using any of our products.

Solvay Specialty Polymers is comprised of the activities of the Solvay Advanced Polymers, Solvay Solexis and Solvay Padanaplast companies along with the Ixan® and Diofan® PVDC products lines. To our actual knowledge, the information contained herein is accurate as of the date of this document. However the companies that comprise Solvay Specialty Polymers and none of their affiliates make any warranty, express or implied, or accepts any liability in connection with this information or its use. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for implantable medical devices; Solvay Specialty Polymers does not allow or support the use of any other products in any implant applications. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. All companies comprising Solvay Specialty Polymers reserve the right to make additions, deletions or modifications to the information at any time without prior notification.

All trademarks and registered trademarks are property of the companies that comprise Solvay Specialty Polymers or their respective owners.
© 2011 Solvay Specialty Polymers. All rights reserved.

